Cross linking time: 15 minutes at 23°C Volume resistivity:

 $>2 10^{15} \Omega$ cm Dielectric strength:

> 23 kV/mm

Specific weight: 1,22 approx

Degree of protection:

IP68 (in proper casings)

Magic Rubber

Fast cross linking bicomponent rubber.

Bicomponent insulating liquid rubber, extremely conformable and fluid, flexible, elastic and re-enterable In just a few minutes, transforms into a rubber with very high dielectric, thermal, mechanical and elastic characteristics.

- For installation up to 1kV
- Low smoke, toxic and corrosive gas emissions
- Ideal also for casts and moulds
- Non toxic and safe



Magic Rubber & Rubber Fluid

Product	Colour	Package type	Total quantity
Magic Rubber 500	•	2 bicomponent bottles 1 measuring cup - 1 mixing palette	500 gr
Magic Rubber 10	•	2 bicomponent tanks 1 measuring cup - 1 mixing palette	10 kg
Rubber Fluid 200	•	Bicomponent single dose bags	200 gr
Rubber Fluid 350	•	Bicomponent single dose bags	350 gr



Mix the 2 components in a ratio of 1:1.



Mix for max 30".



Pour the product into the casing to be filled.



In just a few minutes, the product transforms into rubber.

